

**Auckland Branch**  
 8 Gabador Place,  
 PO Box 22-201, Mt Wellington, Auckland  
**Ph:** 09 270 4247 **Fax:** 09 270 0861  
**Workshop Ph:** 09 270 4266

**Levin Branch**  
 43 Main Road South,  
 Levin 5510  
**Ph:** 06 949 1700  
**Fax:** 06 367 0628

**Hamilton Branch**  
 No 16, Tawa Street Industrial Estate  
 PO Box 837, Hamilton 3240  
**Ph:** 07 843 0890 **Fax:** 07 843 6176

**Christchurch Branch**  
 Cnr Waltham Rd & Mowbray Sts  
 PO Box 30-183, St Martins, Christchurch 8244  
**Ph:** 03 377 1190 **Fax:** 03 365 7510

**Tauranga Branch**  
 99F Aviateion Avenue, Mt Maunganui  
 PO Box 450, Tauranga 3140  
**Ph:** 07 542 9400 **Fax:** 07 542 0983

**Dunedin Branch**  
 14 Neville Street, South Dunedin  
 PO Box 5681, Dunedin  
**Ph:** 03 478 8105 **Fax:** 03 488 2052

## Reinforcing Steel Factors

**Tonnes per m<sup>3</sup>:** 7.850  
**m<sup>3</sup> per tonne:** 0.1274

Bar Diameter	General Data				Bending Information								Approx o/a dia for Deformed Bar	Lap Length (Guide Only)	
					Main Bar					Stirrups					
	Cross Sectional Area (mm <sup>2</sup> )	Vol per m (mm <sup>3</sup> )	Metres per Tonne	Kilograms per metre	Pin Dia	Subtract for bend	Add for Hook	Standard Return (90°)	Min Return (90°)	Pin Dia	Pin Dia	Add for Cut Length			
6	28.27	28274	4505.40	0.2220	30	15	100	100	50	22		140		400	
8	50.27	50265	2534.30	0.3946	40	20	110	130	60	28	32	150		500	
10	78.54	78540	1622.00	0.6165	50	25	120	160	70	32	40	170	12	600	
12	113.1	113097	1126.40	0.8878	60	30	140	200	90	40	50	200	14	750	
16	201.06	201062	633.58	1.5783	80	40	165	260	120	60	70	270	18	1000	
20	314.16	314159	405.49	2.4662	100	45	200	320	150	70	80	400	23	1250	
25	490.87	490874	259.51	3.8534	150	65	280	400	220	Plain	Deformed		29	1600	
32	804.25	804248	158.39	6.3133	200	90	420	520	300					36	2000
40	1256.64	1256637	101.37	9.8646	240	110	500	640	360					45	2500